

AAC Superbond - Technical Data Sheet

Product description

AAC Superbond Adhesive is a graded sand, cement, Calcium Carbonate and additive, dry mixed product for use as a Structural Thin Bed Adhesive for Autoclaved Aerated Concrete substrates. AAC Superbond is designed for use over Autoclaved Aerated Concrete Blocks & Panels. AAC Superbond Adhesive bonds the Autoclaved Aerated Concrete substrates as required for use in Commercial and Residential Applications.

Code Compliance

AAC Superbond corresponds to the relevant parts of AS 3700:2001 "*Masonry Structures*" and the relevant parts of NZS 4229:1999 "*Concrete Masonry Buildings Not Requiring Specific Engineering Design*".

Information which is outside the scope of the above Standards in specific relation to Autoclaved Aerated Concrete construction can be found in the Manufacturers Technical Literature.

Mixing Information

As a guide AAC Superbond Adhesive requires approximately 30% water added (or as required) to achieve the required workable consistency.

1 x 25kg bag = approximately 7.5 litres of water.

Note:

Water ratios given as a guide only.

Water added must be clean potable water.

Water temperature may alter the workable time for this product.

Application Method

AAC Superbond Adhesive is normally applied direct to the substrate using a notched trowel or dredge, Blocks & Panels must be rubbed together to ensure a strong bond has been created.

AAC Superbond Adhesive can also be applied through specialized application machinery.

AAC Superbond Adhesive performs best between 2-3mm thicknesses.

Always refer to Substrate manufacturers Specifications for specific use.

Quality Control

AAC Superbond is manufactured to specification in New Zealand by CFG Coatings Ltd utilising automated weighing and batching equipment in conjunction with a strict quality control regime, the manufacture of this product is guaranteed for the term offered.

Storage

AAC Superbond must be kept dry and sealed, stored off the floor in a manner where moisture cannot come into contact with the bag or its contents. This Product has a shelf life of **6 months** after date of manufacture if stored as detailed above.

Supercoat

Coating Systems

Fresh AAC Superbond Volume – 16.25L of material per 25kg bag when mixed with water.

Fresh Multitex Weight – 1.480kg/L when mixed with water.

Applied to Wall – Yield information must be calculated using the above figure relating to volumes and the dimensions of the substrate being utilised.

*Figures stated on TDS are given as a guide only.

*Adhesion to the substrate varies dependant on the type and relevant densities of the Autoclaved Aerated Concrete being used. In all test cases the AAC Superbond was shown to be stronger than the substrate.

Manufacturer

CFG Coatings Ltd
PO Box 2398, Dunedin, New Zealand.
Phone (03) 456 4222
info@cfg.co.nz



The information contained herein is correct to the best of our knowledge. Due to product improvement and supply, these specifications may be subject to minor changes.