

Deckshield - Technical Data Sheet

Product Description

Supercoat Deckshield is a 100% Acrylic Thixotropic paste with graded aggregate for use on decks and roofs where general foot traffic may be expected. Deckshield is to be used as a final coat for Supercoat Tanking Membrane and is applied via texture gun.

Specifications

MSDS	004 - Version 1.0
Appearance	Grey paste with aggregate
Vehicle Type	100% Acrylic
Pigmentation	Ceramic Pigments
Solvent	Water
Finish	Flat
Colour	Grey
Touch dry time	60 minutes at 20°C
Time to 2nd coat	2 hours at 20°C
Dry film system thickness	1000 - 1500 microns
Solids Content	45% (Silica not included)
Viscosity	95 KU (+/- 3) (Silica not included)
Specific Gravity	1.24 (Silica not included)
Usual number of coats	2
Toxicity	No added Chromites or Lead
Thinning & cleaning	Water
Coverage	0.45m ² /L depending on substrate profile and applicator
Pail type & size	Plastic 4L, 8L & 20L

Please Note

Do not apply at temperatures below 10°C or if it is likely to drop below 10°C during drying/curing time. Softens at temperatures over 70°C. Safe to use on surfaces that collect drinking water.

Manufacturer

CFG Coatings Ltd
PO Box 2398, Dunedin, New Zealand
Phone (03) 456 4222
info@cfg.co.nz



The information contained herein is correct to the best of our knowledge. Due to product improvement and supply, these specifications may be subject to minor changes.